

DIRECTIONS FOR USE

NOTE

- If the pail is to be re-used ensure that it is completely clean before loading fresh material
- Pointing may be carried out as soon as the HeliBond has started to set
- After use, clean all tools, mixers and containers with clean, fresh water

For anchoring applications, a minimum clearance of 2mm all around the component will be adequate but should be increased to overcome drill wander in deeper holes, 500mm+, or to accommodate highly absorbent substrates. For Helifix bars and ties the following will generally apply.



1. Empty the contents of the liquid pack into the pail.
2. Add the contents of the powder pack.
3. Stir thoroughly using a power-driven paddle mixer. Do not attempt to mix by hand as this will result in inadequate mixing.
4. Check the piston is a snug fit in the cartridge and adjust in accordance with the pointing gun instructions. Load the mixture into the cartridge in the pointing gun immediately after agitating.
5. Inject into the slot or hole in a continuous operation. Typical working life of the mixture in the pail is around 2 hours with re-agitation. The cartridge should be emptied within 5 minutes. If the injection process is interrupted for any reason, empty any cartridge contents back into the bucket and re-mix until it again reaches a smooth injectable consistency.